

# UTILITY PATENT APPLICATION TRANSMITTAL

Submit an original and a duplicate for fee processing  
(Only for new nonprovisional applications under 37 CFR §1.53(b))

ADDRESS TO:

Commissioner of Patents and Trademarks  
Box Patent Application  
Washington, D.C. 20231

Attorney Docket No. 207138  
First Named Inventor Yoshio NAKAGAWA  
Express Mail No. EL643537053US

## APPLICATION ELEMENTS

- ☒ Utility Transmittal Form
- ☒ Specification (including claims and abstract) [Total Pages 24]
- ☒ Drawings [Total Sheets 1]
- ☒ Combined Declaration and Power of Attorney [Total Pages 4]
  - ☒ Newly executed
  - ☐ Copy from prior application  
[Note Box 5 below]
    - ☐ Deletion of Inventor(s) Signed statement attached deleting inventor(s) named in the prior application
- ☐ Incorporation by Reference: The entire disclosure of the prior application, from which a copy of the oath or declaration is supplied under Box 4b is considered as being part of the disclosure of the accompanying application and is hereby incorporated by reference therein.
- ☐ Microfiche Computer Program
- ☐ Nucleotide and/or Amino Acid Sequence Submission
  - ☐ Computer Readable Copy
  - ☐ Paper Copy
  - ☐ Statement verifying above copies

## ACCOMPANYING APPLICATION PARTS

- ☐ Assignment Papers (cover sheet and document(s))
- ☐ Power of Attorney
- ☐ English Translation Document (if applicable)
- ☐ Information Disclosure Statement (IDS)
  - ☐ Form PTO-1449
  - ☐ Copies of References
- ☒ Preliminary Amendment
- ☒ Return Receipt Postcard (Should be specifically itemized)
- ☐ Small Entity Statement(s)
  - ☐ Enclosed
  - ☐ Statement filed in prior application; status still proper and desired
- ☒ Certified Copy of Priority Document(s)
- ☒ Other: Print EFS [2 pages]; Pending Claims as of November 3, 2000 [3 pages]

17. If a CONTINUING APPLICATION, check appropriate box and supply the requisite information in (a) and (b) below:

- ☐ Continuation ☐ Divisional ☐ Continuation-in-part of prior application Serial No. \_\_\_\_\_  
Prior application information: Examiner \_\_\_\_\_; Group Art Unit: \_\_\_\_\_
- Preliminary Amendment: Relate Back - 35 USC §120. The Commissioner is requested to amend the specification by inserting the following sentence before the first line:  
"This is a ☐ continuation ☐ divisional of copending application(s)  
☐ Application No. \_\_\_\_\_, filed on \_\_\_\_\_  
☐ International Application, filed on \_\_\_\_\_, and which designates the U.S."

## APPLICATION FEES

APPLICATION FEES				
BASIC FEE				\$710.00
CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE	
Total Claims	20 -20=	0	x \$18.00	\$0.00
Independent Claims	2 -3=	0	x \$80.00	\$0.00
<input type="checkbox"/> Multiple Dependent Claim if applicable			+\$270.00	\$0.00
Total of above calculations =				\$710.00
Reduction by 50% for filing by small entity =				\$(0.00)
<input type="checkbox"/> Assignment fee if applicable			+\$40.00	\$0.00
TOTAL =				\$710.00

## UTILITY PATENT APPLICATION TRANSMITTAL

Attorney Docket No. 207138

19. ☐ Please charge my Deposit Account No. 12-1216 in the amount of \$ .
20. ☒ A check in the amount of \$710.00 is enclosed.
21. The Commissioner is hereby authorized to credit overpayments or charge any additional fees of the following types to Deposit Account No. 12-1216:
- a. ☒ Fees required under 37 CFR §1.16.
- b. ☒ Fees required under 37 CFR §1.17.
22. ☐ The Commissioner is hereby generally authorized under 37 CFR §1.136(a)(3) to treat any future reply in this or any related application filed pursuant to 37 CFR §1.53 requiring an extension of time as incorporating a request therefor, and the Commissioner is hereby specifically authorized to charge Deposit Account No. 12-1216 for any fee that may be due in connection with such a request for an extension of time.

jc931 U.S. PRO  
09/705838

## 23. CORRESPONDENCE ADDRESS

☒ Customer Number: 23460**23460**

PATENT TRADEMARK OFFICE

☐ John Kilyk, Jr., Reg. No. 30,763  
Leydig, Voit & Mayer, Ltd.  
Two Prudential Plaza, Suite 4900  
180 North Stetson  
Chicago, Illinois 60601-6780  
(312) 616-5600 (telephone)  
(312) 616-5700 (facsimile)

Name	John Kilyk, Jr., Registration No. 30,763
Signature	
Date	November 3, 2000

## Certificate of Mailing Under 37 CFR §1.10

I hereby certify that this Utility Patent Application Transmittal and all accompanying documents are being deposited with the United States Postal Service "Express Mail Post Office To Addressee" Service under 37 CFR §1.10 on the date indicated below and is addressed to: Commissioner of Patents and Trademarks, Box Patent Application, Washington, D.C. 20231

*Rick O. Madson*

Name of Person Signing

*Rick O. Madson*

Signature

November 3, 2000

Date

Figure 1 consists of 12 bar charts, labeled (a) through (l), each representing a different variable. Each chart compares two groups: 'No' (represented by white bars) and 'Yes' (represented by black bars). The y-axis for all charts represents the percentage of respondents, ranging from 0 to 100.

- (a) Age:** The 'No' group is predominantly older (60+), while the 'Yes' group is predominantly younger (18-39).
- (b) Sex:** The 'No' group is predominantly male, while the 'Yes' group is predominantly female.
- (c) Education:** The 'No' group is predominantly high school or less, while the 'Yes' group is predominantly college or higher.
- (d) Income:** The 'No' group is predominantly lower income, while the 'Yes' group is predominantly higher income.
- (e) Employment:** The 'No' group is predominantly unemployed, while the 'Yes' group is predominantly employed.
- (f) Home ownership:** The 'No' group is predominantly does not own, while the 'Yes' group is predominantly owns.
- (g) Religion:** The 'No' group is predominantly Catholic, while the 'Yes' group is predominantly Protestant.
- (h) Political affiliation:** The 'No' group is predominantly Republican, while the 'Yes' group is predominantly Democrat.
- (i) Party affiliation:** The 'No' group is predominantly Republican, while the 'Yes' group is predominantly Democrat.
- (j) Attitude towards gay people:** The 'No' group is predominantly negative, while the 'Yes' group is predominantly positive.
- (k) Attitude towards gay people (stronger):** The 'No' group is predominantly negative, while the 'Yes' group is predominantly positive.
- (l) Attitude towards gay people (weaker):** The 'No' group is predominantly negative, while the 'Yes' group is predominantly positive.

Inventor One Given Name:: Yoshio  
Family Name:: Nakagawa  
Postal Address Line One:: c/o Nitto Denko Corporation  
Postal Address Line Two:: 1-2, Shimohozumi 1-chome  
City:: Ibaraki-shi  
State or Province:: Osaka  
Country:: Japan  
Postal or Zip Code:: 567-8680  
Citizenship Country:: Japan  
Inventor Two Given Name:: Shigeki  
Family Name:: Ishiguro  
Postal Address Line One:: c/o Nitto Denko Corporation  
Postal Address Line Two:: 1-2, Shimohozumi 1-chome  
City:: Ibaraki-shi  
State or Province:: Osaka  
Country:: Japan  
Postal or Zip Code:: 567-8680  
Citizenship Country:: Japan  
Inventor Three Given Name:: Masayoshi  
Family Name:: Natsume  
Postal Address Line One:: c/o Nitto Denko Corporation  
Postal Address Line Two:: 1-2, Shimohozumi 1-chome  
City:: Ibaraki-shi  
State or Province:: Osaka  
Country:: Japan  
Postal or Zip Code:: 567-8680  
Citizenship Country:: Japan  
Inventor Four Given Name:: Shinichi  
Family Name:: Takada  
Postal Address Line One:: c/o Nitto Denko Corporation  
Postal Address Line Two:: 1-2, Shimohozumi 1-chome  
City:: Ibaraki-shi  
State or Province:: Osaka  
Country:: Japan  
Postal or Zip Code:: 567-8680  
Citizenship Country:: Japan  
Inventor Five Given Name:: Kooki  
Family Name:: Ooyama  
Postal Address Line One:: c/o Nitto Denko Corporation  
Postal Address Line Two:: 1-2, Shimohozumi 1-chome  
City:: Ibaraki-shi  
State or Province:: Osaka  
Country:: Japan  
Postal or Zip Code:: 567-8680  
Citizenship Country:: Japan  
Inventor Six Given Name:: Hajime  
Family Name:: Yanagida  
Postal Address Line One:: c/o Nitto Denko Corporation





In re Appln. of Nakagawa et al.  
Application No. Unassigned

8. (Amended) The adhesive tape of claim 1 [or claim 2], wherein the flame retardant is added in an amount of 20 - 200 parts by weight per 100 parts by weight of the olefin polymer.

9. (Amended) The adhesive tape of claim 1 [or claim 2], wherein the flame retardant is a metal hydroxide.

10. (Amended) The adhesive tape of claim 1 [or claim 2], which has a dynamic storage modulus (E') at 80°C of not less than 25 MPa and a dynamic storage modulus (E') at 120°C of not less than 10 MPa.

11. (Amended) The adhesive tape of claim 1 [or claim 2], wherein the substrate is not crosslinked during or after a forming process thereof.

#### REMARKS

The claims have been amended to remove multiple claim dependencies. Specifically, original multiply-dependent claims 3 and 8 - 11 have been amended to be singly-dependent. After entry of these claim amendments, claims 1-20 remain pending. For the convenience of the Examiner, the text of the pending claims after amendment is set forth on an attachment hereto.

The application is considered in good and proper form for allowance, and the Examiner is respectfully requested to pass this application to issue. If, in the opinion of the Examiner, a telephone conference would expedite the prosecution of the subject application, the Examiner is invited to call the undersigned attorney.

Figure 1 consists of 12 bar charts, labeled (a) through (l), each representing a different variable. Each chart compares the percentage of Clinton supporters (n=100) and Clinton opponents (n=100) for that variable. The y-axis for all charts ranges from 0 to 100 percent.

- (a) Age:** Clinton supporters are more likely to be 18-29 (40% vs 30%) and 30-49 (40% vs 35%). Clinton opponents are more likely to be 50-59 (35% vs 25%) and 60+ (25% vs 15%).
- (b) Sex:** Clinton supporters are more likely to be female (55% vs 45%). Clinton opponents are more likely to be male (55% vs 45%).
- (c) Education:** Clinton supporters are more likely to have a high school diploma or less (45% vs 35%) and a college degree (55% vs 45%). Clinton opponents are more likely to have a high school diploma or less (45% vs 35%) and a college degree (55% vs 45%).
- (d) Income:** Clinton supporters are more likely to have an income of \$10,000 or less (45% vs 35%) and \$10,000-\$20,000 (45% vs 35%). Clinton opponents are more likely to have an income of \$20,000-\$30,000 (35% vs 25%) and \$30,000 or more (25% vs 15%).
- (e) Employment:** Clinton supporters are more likely to be employed (65% vs 55%). Clinton opponents are more likely to be unemployed (35% vs 25%).
- (f) Home ownership:** Clinton supporters are more likely to own their home (65% vs 55%). Clinton opponents are more likely to not own their home (35% vs 25%).
- (g) Marital status:** Clinton supporters are more likely to be married (65% vs 55%). Clinton opponents are more likely to be single (35% vs 25%).
- (h) Political affiliation:** Clinton supporters are more likely to be Democrat (85% vs 75%). Clinton opponents are more likely to be Republican (15% vs 25%).
- (i) Party identification:** Clinton supporters are more likely to identify with the Democratic Party (85% vs 75%). Clinton opponents are more likely to identify with the Republican Party (15% vs 25%).
- (j) Trust in Clinton:** Clinton supporters are more likely to trust Clinton (85% vs 75%). Clinton opponents are more likely to not trust Clinton (15% vs 25%).
- (k) Confidence in Clinton:** Clinton supporters are more likely to have confidence in Clinton (85% vs 75%). Clinton opponents are more likely to not have confidence in Clinton (15% vs 25%).
- (l) Confidence in Gore:** Clinton supporters are more likely to not have confidence in Gore (85% vs 75%). Clinton opponents are more likely to have confidence in Gore (15% vs 25%).

*[Signature]*  
Kryk Ir Reg No 30763

Date: November 3, 2000

**IN THE UNITED STATES PATENT AND TRADEMARK OFFICE**

In re Application of:

Nakagawa et al.

Art Unit: Unassigned

Application No. Unassigned

Examiner: Unassigned

Filed: October 31, 2000

For: ADHESIVE TAPE AND SUBSTRATE FOR  
ADHESIVE TAPE

**PENDING CLAIMS AS OF NOVEMBER 3, 2000**

1. An adhesive tape comprising a substrate and an adhesive layer formed on at least one side of the substrate, wherein the substrate comprises an olefin polymer and a flame retardant, but substantially no halogen atom, and the adhesive tape has a thermal deformation at 100°C of not more than 65%.

2. The adhesive tape of claim 1, which has an elongation at break of not less than 150% at a tension speed of 300 mm/min.

3. The adhesive tape of claim 1, wherein the olefin polymer comprises the following Component A and Component B:

Component A: a thermoplastic resin having a carbonyl oxygen atom in the molecular skeleton

Component B: a polymer alloy containing an ethylene component and a propylene component.

4. The adhesive tape of claim 3, wherein the Component B has a dynamic storage modulus (E') at 80°C of not less than 40 MPa and less than 180 MPa, and a dynamic storage modulus (E') at 120°C of not less than 12 MPa and less than 70 MPa.

09706530-110300



5. The adhesive tape of claim 3, wherein the Component B has a dynamic storage modulus ( $E'$ ) at 23°C of not less than 200 MPa and less than 400 MPa.
6. The adhesive tape of claim 3, wherein the Component A is an ethylene copolymer or a metal salt thereof, having a melting point of not more than 120°C, which is obtained by polymerizing a vinyl ester compound, or an  $\alpha$ ,  $\beta$ -unsaturated carboxylic acid or a derivative thereof, or the vinyl ester compound and the  $\alpha$ ,  $\beta$ -unsaturated carboxylic acid or a derivative thereof.
7. The adhesive tape of claim 3, wherein the Component A and the Component B are mixed at a weight ratio (A:B) of 1:9 - 8:2.
8. The adhesive tape of claim 1, wherein the flame retardant is added in an amount of 20 - 200 parts by weight per 100 parts by weight of the olefin polymer.
9. The adhesive tape of claim 1, wherein the flame retardant is a metal hydroxide.
10. The adhesive tape of claim 1, which has a dynamic storage modulus ( $E'$ ) at 80°C of not less than 25 MPa and a dynamic storage modulus ( $E'$ ) at 120°C of not less than 10 MPa.
11. The adhesive tape of claim 1, wherein the substrate is not crosslinked during or after a forming process thereof.
12. A substrate for an adhesive tape, which comprises an olefin polymer and a flame retardant, but substantially no halogen atom, wherein the olefin polymer comprises the following Component A and Component B:  
Component A: a thermoplastic resin having a carbonyl oxygen atom in the molecular skeleton

Component B: a polymer alloy containing an ethylene component and a propylene component.

13. The substrate of claim 12, wherein the Component B has a dynamic storage modulus ( $E'$ ) at 80°C of not less than 40 MPa and less than 180 MPa, and a dynamic storage modulus ( $E'$ ) at 120°C of not less than 12 MPa and less than 70 MPa.

14. The substrate of claim 12, wherein the Component B has a dynamic storage modulus ( $E'$ ) at 23°C of not less than 200 MPa and less than 400 MPa.

15. The substrate of claim 12, wherein the Component A is an ethylene copolymer or a metal salt thereof, having a melting point of not more than 120°C, which is obtained by polymerizing a vinyl ester compound, or an  $\alpha$ ,  $\beta$ -unsaturated carboxylic acid or a derivative thereof, or the vinyl ester compound and the  $\alpha$ ,  $\beta$ -unsaturated carboxylic acid or a derivative thereof.

16. The substrate of claim 12, wherein the Component A and the Component B are mixed at a weight ratio (A:B) of 1:9 - 8:2.

17. The substrate of claim 12, wherein the flame retardant is added in an amount of 20 - 200 parts by weight per 100 parts by weight of the olefin polymer.

18. The substrate of claim 12, wherein the flame retardant is a metal hydroxide.

19. The substrate of claim 12, which has a dynamic storage modulus ( $E'$ ) at 80°C of not less than 25 MPa and a dynamic storage modulus ( $E'$ ) at 120°C of not less than 10 MPa.

20. The substrate of claim 12, which is not crosslinked during or after a forming process thereof.





an adhesive tape having a high level of stretchability that is beneficial in winding a tape, in addition to high levels of the resistance to thermal deformation and flame resistance, as well as a substrate to be used for this adhesive tape.

#### SUMMARY OF THE INVENTION

According to the present invention, a thermoplastic resin having a carbonyl oxygen atom in the molecular skeleton and a polymer alloy containing an ethylene component and a propylene component, in combination, are used as an olefin polymer, and a flame retardant is added to give a substrate. As a result, a substrate for an adhesive tape, which shows high levels of resistance to thermal deformation and stretchability, as well as a high level of flame resistance, can be obtained.

Accordingly, the present invention provides an adhesive tape comprising a substrate and an adhesive layer formed on at least one side of the substrate, wherein the substrate comprises an olefin polymer and a flame retardant, but substantially no halogen atom, and the adhesive tape shows a thermal deformation at 100°C of not more than 65%.

In a preferable embodiment, the adhesive tape shows the following properties. It shows an elongation at break of not less than 150% at a tension speed of 300 mm/min. It shows a dynamic storage modulus (E') at 80°C of not less than 25 MPa and a dynamic storage modulus (E') at 120°C of not less than 10 MPa.

The present invention provides a substrate for an adhesive tape, which contains an olefin polymer and a flame retardant but contains substantially no halogen atom, wherein the olefin polymer contains the following Component A and Component B:

Component A: a thermoplastic resin having a carbonyl oxygen atom in the molecular skeleton

Component B: a polymer alloy containing an ethylene component and a propylene component

In a preferable embodiment, the Component B shows the following properties. It shows a dynamic storage modulus (E') at 80°C of not less than 40 MPa and less than 180 MPa, and a dynamic storage modulus (E') at 120°C of not less than 12 MPa and less than 70 MPa. It shows a dynamic storage modulus (E') at 23°C of not less than 200 MPa and less than 400 MPa.

Component A is an ethylene copolymer having a melting point of not more than 120°C, which is obtained by polymerizing a vinyl ester compound and/or  $\alpha,\beta$ -unsaturated carboxylic acid or a derivative thereof, or a metal salt of the ethylene copolymer.

5 Component A and Component B are mixed at a weight ratio (A:B) of 1:9 - 8:2. The flame retardant is added in an amount of 20 - 200 parts by weight per 100 parts by weight of an olefin polymer. The flame retardant is a metal hydroxide.

10 In another preferable embodiment, the substrate has a dynamic storage modulus ( $E'$ ) at 80°C of not less than 25 MPa, and a dynamic storage modulus ( $E'$ ) at 120°C of not less than 10 MPa. The substrate is not crosslinked during or after its formation.

#### BRIEF DESCRIPTION OF THE DRAWINGS

15 Fig. 1(a) and Fig. 1(b) show a method for the evaluation of thermal deformation of an adhesive tape, wherein Fig. 1(a) is a side view of the test sample, Fig. 1(b) is a side view of a test apparatus, 1 is a round bar, 2 is a loading plate, 2a is a convex, 3 is a parallel plate, 10 is a test sample and T is an  
20 adhesive tape.

#### DETAILED DESCRIPTION OF THE INVENTION

The adhesive tape of the present invention comprises a substrate containing an olefin polymer and a flame retardant, but contains substantially no halogen atom, and an adhesive  
25 layer formed at least on one side of the substrate. The adhesive tape has a thermal deformation at 100°C of not more than 65% (preferably not more than 40%, particularly preferably 0%), and preferably the thermal deformation of not more than 65% together with an elongation at break of not less than 150%  
30 (preferably 170-500%) at a tension speed of 300 mm/min.

As used herein, by the "substantially no halogen atom" is meant non-use of a substance having a halogen atom in a molecule as a material of the substrate. However, a halogen atom detected in an ultra-trace amount by analysis of the composition  
35 of a tape substrate using mechanical analysis means is excluded. For example, a halogen atom may be contained in an ultra-trace amount in the substrate, due to the use of a halogen-containing substance as a catalyst for the synthesis of a constituting

material.

A thermal deformation at 100°C and an elongation at break (%) at a tension speed of 300 mm/min of the adhesive tape are respectively used as indices of resistance to thermal deformation and stretchability of the tape. An adhesive tape having a thermal deformation at 100°C of not more than 65% shows a high level of resistance to thermal deformation in actual use (adhered to a target object). An adhesive tape having an elongation at break of not less than 150% at a tension speed of 300 mm/min shows a high level of stretchability. Therefore, the tape can be easily stretched in actual use (adhered to a target object (winding)) and the adhesion (winding) can be performed with superior workability. The thermal deformation and the elongation at break of the adhesive tape were measured by the following method.

#### Measurement method of thermal deformation

Measured according to UL-510. As shown in Figure 1(a), an adhesive tape T is wound around a round conductor bar 1 having a diameter (d) of 2 mm and a length of 30 mm to prepare a test sample 10. The outer diameter (D0) of the test sample 10 at normal temperature is measured with a dial gauge defined in JIS B 7503, vernier calipers defined in JIS B 7507, or a measurement tool having the same degree of measurement precision. The test sample 10 is placed in a tester heated to a predetermined temperature (100°C±1.0°C) and heated for 60 minutes. The test sample is placed between a loading plate 2 having a columnar convex 2a having a diameter of 9.5±0.2 mm and a parallel plate 3, as shown in Figure 1(b), pressurized (4.9 N) from the vertical direction of the planar surface of the plates and left standing at a predetermined temperature (100°C±1.0°C) for 60 minutes. The test sample is measured for the outer diameter (D1) *in situ*. The thickness (t0) before heating the tape and the thickness (t1) after heating the tape are calculated from the following formula (II). A decrease in the thickness (thermal deformation (X)) of the tape is calculated from the following formula (III):

$$t=(D-d)/2 \quad (II)$$

wherein D is an outer diameter of the test sample and d is

a diameter of the round bar,

$$X(\%) = \{(t_0 - t_1) / t_0\} \times 100 \quad (\text{III})$$

wherein  $t_0$  is a thickness (mm) before heating and  $t_1$  is a thickness (mm) after heating.

5 Measurement method of elongation at break

10 A test piece (width 19 mm, length 100 mm) taken from an adhesive tape prepared by forming a 30  $\mu\text{m}$  thick adhesive layer on one side of a 0.2 mm thick substrate is held at both ends in the length direction thereof at 23°C, 60% RH, wherein the length direction is the direction of flow during forming a substrate (MD direction), and stretched at a tension speed of 300 mm/min in the length direction by a universal tensile compression tester to measure elongation at break (%).

15 In the present invention, an adhesive tape having a thermal deformation at 100°C of not more than 65% can be obtained by using Component A and Component B to be mentioned later as olefin polymers together with a flame retardant, by appropriately determining the kind, mixing weight ratio, combination and the like of Component A and Component B, by  
20 using Component B having a specific dynamic storage modulus ( $E'$ ), by using Component A having a specific melting point, and the like. This also applies to an adhesive tape having a thermal deformation of not more than 65% and an elongation at break of not less than 150% at a tension speed of 300 mm/min.

25 In the present invention, the olefin polymer constituting a tape substrate can be used without any particular limitation as long as a mixture of the olefin polymer and a flame retardant in an amount to bring about sufficient flame resistance can impart desired superior resistance to thermal deformation and  
30 stretchability to an adhesive tape. An olefin polymer mainly containing the following Component A and Component B is preferable.

Component A: a thermoplastic resin having a carbonyl oxygen atom in the molecular skeleton

35 Component B: a polymer alloy containing an ethylene component and a propylene component

The thermoplastic resin having a carbonyl oxygen atom (oxygen atom attributable to carbonyl) in the molecular skeleton



of Component A activates a flame resistance-imparting action by a flame retardant and imparts appropriate flexibility and fine stretchability to a substrate (adhesive tape). Particularly, a soft polyolefin resin having a carbonyl oxygen atom in the molecular skeleton is preferable. The soft polyolefin resin having a carbonyl oxygen atom in the molecular skeleton may be an ethylene copolymer or a metal salt thereof (particularly ionomer) comprising a vinyl ester compound and/or an  $\alpha,\beta$ -unsaturated carboxylic acid or a derivative thereof as a monomer or a comonomer. In general, it has a melting point of not more than 120°C, preferably 40-100°C. The melting point is measured by a differential scanning calorimeter (DSC).

In the above-mentioned ethylene copolymer or a metal salt thereof (particularly ionomer), the vinyl ester compound may be, for example, lower alkyl ester of vinyl alcohol such as vinyl acetate and the like. The  $\alpha,\beta$ -unsaturated carboxylic acid or a derivative thereof may be, for example, unsaturated carboxylic acids and anhydrides thereof, such as acrylic acid, methacrylic acid, maleic acid, fumaric acid, maleic anhydride, itaconic anhydride and the like; unsaturated carboxylates such as methyl acrylate, methyl methacrylate, ethyl acrylate, ethyl methacrylate, propyl acrylate, propyl methacrylate, isopropyl acrylate, isopropyl methacrylate, n-butyl acrylate, n-butyl methacrylate, cyclohexyl acrylate, cyclohexyl methacrylate, stearyl acrylate, stearyl methacrylate, lauryl acrylate, lauryl methacrylate, monomethyl maleate, monoethyl maleate, diethyl maleate, monomethyl fumarate, glycidyl acrylate and glycidyl methacrylate; and the like. Of these, alkyl (meth)acrylate, particularly ethyl acrylate, is preferable.

Examples of suitable ethylene copolymer or a metal salt thereof (particularly ionomer) include ethylene-acrylic acid copolymer, ethylene-methacrylic acid copolymer, ethylene-ethyl acrylate copolymer, ethylene-acrylic acid-ethyl acrylate copolymer, ethylene-vinyl acetate-copolymer, ethylene-vinyl acetate-ethyl acrylate copolymer, ethylene-glycidyl methacrylate copolymer, ethylene-glycidyl methacrylate-ethyl acrylate copolymer and a metal salt thereof (particularly ionomer) and the like, which may be used alone or in combination.

The effect of activating a flame resistance-imparting action of a flame retardant by the thermoplastic resin having a carbonyl oxygen atom in the molecular skeleton of Component A cannot be achieved by a thermoplastic resin without a carbonyl oxygen atom in the molecular skeleton.

The polymer alloy containing an ethylene component and a propylene component of Component B mainly suppresses thermal deformation of a substrate (adhesive tape). By making an alloy of an ethylene component and a propylene component, the polymer alloy shows viscoelasticity suitable for suppressing thermal deformation of particularly a substrate (adhesive tape).

The constitution (form) of the polymer alloy is not particularly limited. For example, various constitutions (forms) are acceptable such as (1) a polymer blend (physical mixture) of two or more kinds of polymers physically mixed, (2) a block copolymer or graft copolymer wherein two or more kinds of polymers are bonded by a covalent bond, and (3) an IPN (Interpenetrating Polymer Network) structure wherein two or more kinds of polymers are intertwined without a covalent bond.

The polymer alloy may not be homogeneous in composition but may have a distribution. In addition, it may be an alloy of two or more kinds of compatible polymers or a phase separation structure formed by two or more kinds of incompatible polymers. It may have a thermal property showing plural exothermic or endothermic peaks by DSC measurement.

Examples of the polymer alloy containing an ethylene component and a propylene component of Component B include a physical mixture of polypropylene (homo polypropylene, random polypropylene) and polyethylene (inclusive of copolymer of ethylene and a small amount of other  $\alpha$ -olefin), propylene/ethylene copolymer (block copolymer or graft copolymer), terpolymer of propylene, ethylene and  $\alpha$ -olefin other than these, and the like. As used herein, by the above-mentioned other  $\alpha$ -olefin is meant 1-butene, 1-penten, 1-hexene, 4-methyl-1-pentene, 1-heptene, 1-octene and the like, with preference given to 1-butene. By the homo polypropylene is meant a polymer comprising substantially 100% of propylene and by the random polypropylene is meant a copolymer comprising

several percent of ethylene randomly copolymerized.

When the polymer alloy is a copolymer, a copolymer obtained by multi-step polymerization involving two or more steps is preferable, with preference given to a

5 propylene/ethylene copolymer. The copolymer obtained by multi-step polymerization involving two or more steps can be obtained by, as disclosed in JP-A-4-224809, for example, preliminarily polymerizing propylene or propylene and  $\alpha$ -olefin other than propylene in the presence of a titanium compound and an organic  
10 aluminum compound as catalysts in the first step of the multi-step polymerization, and then copolymerizing propylene and ethylene (after addition of  $\alpha$ -olefin other than propylene and ethylene as necessary) in the presence of the produced titanium-containing polyolefin and an organic aluminum compound in the  
15 second step or a subsequent step. As a result, the obtained is a copolymer of a polymer produced in the first step [e.g., polypropylene (homopolymer of propylene), propylene- $\alpha$ -olefin copolymer and the like] and a polymer produced in the second step or a subsequent step (e.g., propylene-ethylene copolymer,  
20 propylene-ethylene-other  $\alpha$ -olefin copolymer, and the like), which copolymer has been blended to a molecular level in the second step or a subsequent step. The above-mentioned titanium compound is, for example, a solid catalyst having an average particle size of 15  $\mu\text{m}$  and is obtained by pulverizing titanium  
25 trichloride and magnesium chloride together, and treating with n-butyl orthotitanate, 2-ethylhexanol, ethyl p-toluate, silicon tetrachloride, diisobutyl phthalate and the like. The organic aluminum compound may be, for example, alkyl aluminum such as triethyl aluminum and the like. In a polymerized phase, a  
30 silicon compound such as diphenyldimethoxysilane and the like or an iodine compound such as ethyl iodide may be contained as an electron donor.

The polymer alloy containing an ethylene component and a propylene component of Component B preferably shows high  
35 elasticity under high temperature, that is, in consideration of the temperature during use of the adhesive tape, it preferably shows a dynamic storage modulus ( $E'$ ) at 80°C of not less than 40 MPa and less than 180 MPa (preferably within the range of 45 -

160 MPa) and a dynamic storage modulus (E') at 120°C of not less than 12 MPa and less than 70 MPa (preferably within the range of preferably 15 - 65 MPa). The above-mentioned dynamic storage modulus (E') sufficiently suppresses thermal deformation of a substrate (adhesive tape).

The dynamic storage modulus (E') here is measured in the following manner. That is, a polymer alloy test piece (thickness 0.2 mm: width 10 mm, length 20 mm) is prepared, and the dynamic viscoelastic behavior of this test piece at dispersed temperatures is measured with DMS200 (trademark, manufactured by Seiko Instruments) as a measurement apparatus under the measurement conditions of method: extension mode, temperature rise: 2°C/min, frequency: 1 Hz.

Examples of the polymer alloy showing such dynamic storage modulus (E') include trademarks CATALLOY KS-353P, CATALLOY KS-021P and CATALLOY C200F manufactured by Montell SKD Sunrise Ltd., and the like.

The polymer alloy of Component B preferably shows a dynamic storage modulus (E') at 23°C of not less than 200 MPa and less than 400 MPa in consideration of the workability of the adhesive tape at near room temperature (followability of the adhesive tape to the object to be adhered to). The dynamic storage modulus (E') of this range of the polymer alloy of Component B leads to fine flexibility of the substrate, and therefore, improved followability to the object to be adhered to. The dynamic storage modulus (E') here is measured by the aforementioned method. Examples of the polymer alloy having such dynamic storage modulus (E') include trademarks CATALLOY KS-353P, CATALLOY KS-021P and CATALLOY C200F manufactured by Montell SKD Sunrise Ltd., and the like.

Component A (a thermoplastic resin having a carbonyl oxygen atom in the molecular skeleton) and Component B (a polymer alloy containing an ethylene component and a propylene component) are mixed at a weight ratio (A:B) of generally 1:9 - 8:2, preferably 2:8 - 6:4. When the weight ratio is outside this range and Component A is used in a smaller amount (Component B is in a greater amount), the substrate may be poor in flexibility, stretchability and flame resistance. When

Component A is used in a greater amount (Component B is in a smaller amount), the substrate may show poor resistance to thermal deformation.

In the present invention, the flame retardant may be, for example, metal hydroxide such as aluminum hydroxide, magnesium hydroxide, zirconium hydroxide, calcium hydroxide, barium hydroxide and the like; metal carbonate such as basic magnesium carbonate, magnesium calcium carbonate, calcium carbonate, barium carbonate, dolomite and the like; metal hydrate (hydrate of metal compound) such as hydrotalcite, borax and the like; barium metaborate, magnesium oxide and the like. These may be used alone or in combination. Of these, one selected from the group of metal hydroxide such as aluminum hydroxide, magnesium hydroxide, zirconium hydroxide, calcium hydroxide, barium hydroxide and the like, basic magnesium carbonate and hydrotalcite, particularly the above-mentioned metal hydroxide, is advantageous in view of flame resistance-imparting effect and economical aspect.

The flame retardant has a particle size that varies depending on the kind of compound. For example, a metal hydroxide, such as aluminum hydroxide, magnesium hydroxide and the like, has an average particle size of about 0.1 - 50  $\mu\text{m}$ , preferably 0.5 - 20  $\mu\text{m}$ . The particle size here is measured by a laser diffraction method.

The flame retardant is added in an amount of generally 20 - 200 parts by weight, preferably 40 - 150 parts by weight, per 100 parts by weight of the olefin polymer. When the amount added of the flame retardant is outside this range and is smaller, sufficient flame resistance cannot be imparted to the substrate (adhesive tape). When it is greater, the substrate (adhesive tape) may become poor in flexibility and stretchability.

With the purpose of encouraging charring of a flame retardant to give a carbonized layer, red phosphorus may be used. When using red phosphorus, to prevent generation of toxic phosphine even when red phosphorus is heated in the presence of water (stabilization of surface of red phosphorus), red phosphorus may be coated with a film made from metal hydroxide selected

from aluminum hydroxide, magnesium hydroxide, zinc hydroxide and titanium hydroxide. Alternatively, a film of a thermosetting resin (phenol resin and the like) may be formed on the metal hydroxide film to cover red phosphous in duplicate. A char forming auxiliary containing such red phosphous is suitably added in a proportion of generally 2 - 10 parts by weight, preferably 4 - 8 parts by weight, per 100 parts by weight of the olefin polymer.

When a char forming auxiliary containing red phosphous is used, at least one member selected from carbon black, borates and silicone compounds (silicone oil, silicone rubber, silicone resin and the like) is concurrently used to secure a more preferable effect. In this case, at least one member selected from carbon black, borates and silicone compounds is added in an amount of generally 0.5 - 10 wt%, preferably 1 - 5 wt%, per 100 parts by weight of the olefin polymer.

In the present invention, the substrate consists of an olefin polymer and a flame retardant as essential components. Where necessary, an inorganic filler such as titanium oxide, zinc oxide and the like, an age resister and antioxidant such as amine type, quinoline type, hydroquinone type, phenol type, phosphorous type and phosphite type age resisters and the like, an ultraviolet absorber such as salicylic acid derivative, benzophenone type, benzotriazole type and hindered amine type ultraviolet absorbers and the like, a lubricant, a plasticizer and the like may be added.

According to the present invention, the substrate is generally obtained by dry blending a polyolefin polymer, a flame retardant and a substance added as necessary such as filler and the like, kneading the mixture in a Banbury mixer, a roller, an extruder and the like, and forming the kneaded mixture into a film by a known forming method such as compression forming, calendar forming, injection forming, extrusion forming and the like. The substrate (film) has a thickness of generally 0.01 - 1 mm, preferably 0.05 - 0.5 mm, though subject to change depending on the use of the adhesive tape.

After film forming, the substrate of the present invention preferably does not undergo a crosslinking treatment comprising

an ionizing radiation such as electron beam,  $\beta$ -ray,  $\gamma$ -ray and the like, after film forming, or a crosslinking treatment comprising addition, during forming process, of a crosslinking agent, such as organic peroxide and the like, or a crosslinking auxiliary to the material to be formed. In other words, the whole substrate is preferably free of crosslinking structure.

The adhesive tape of the present invention is produced by forming an adhesive layer at least on one side of the above-mentioned substrate. Examples of the adhesive include any adhesive, such as rubber type, hot melt type, acrylic type and emulsion type adhesives, which is currently in use. Examples of preferable base polymer of the rubber and hot melt adhesives include natural rubber, regenerated rubber, silicone rubber, isoprene rubber, styrene-butadiene rubber, polyisoprene, NBR, styrene-isoprene copolymer, styrene-isoprene-butadiene copolymer and the like.

Examples of the tackifier to be used for adhesive include rosin tackifier, terpene tackifier, aliphatic petroleum hydrocarbon (C5) tackifier, aliphatic petroleum hydrocarbon (C9) tackifier, hydrogenated compound and the like. It is also possible to add an additive usually added to the adhesive for an adhesive tape, such as oil, wax, antioxidant and the like in an amount determined by a conventional method.

Of the aforementioned adhesives, an acrylic adhesive is preferable. Examples thereof include homopolymer of (meth)acrylate or a copolymer thereof with a copolymerizable monomer. Examples of (meth)acrylate and the copolymerizable monomer include alkyl (meth)acrylate (e.g., methyl ester, ethyl ester, butyl ester, 2-ethylhexyl ester, octyl ester and the like), glycidyl (meth)acrylate, (meth)acrylic acid, itaconic acid, maleic anhydride, (meth)acrylamide, (meth)acrylic N-hydroxyamide, alkylaminoalkyl (meth)acrylate (e.g., dimethylaminoethyl methacrylate, t-butylaminoethyl methacrylate and the like), vinyl acetate, styrene, acrylonitrile and the like. Of these, the main monomer is preferably alkyl acrylate wherein its homopolymer (single polymer) generally has a glass transition temperature of not more than  $-50^{\circ}\text{C}$ .

The adhesive is applied by a conventionally-known method

such as cast method, roll coater method, reverse coater method, doctor blade method and the like.

The adhesive layer has a thickness (thickness after drying) that varies depending on the use of the adhesive tape, which is generally 10 - 50  $\mu\text{m}$ , preferably 15 - 40  $\mu\text{m}$ .

In the present invention, the adhesive tape preferably has a dynamic storage modulus ( $E'$ ) at 80°C of not less than 25 MPa and a dynamic storage modulus ( $E'$ ) at 120°C of not less than 10 MPa. Such dynamic storage moduli make the substrate (adhesive tape) less likely suffer from thermal deformation. In view of the suitable flexibility and stretchability necessary for an adhesive tape, the dynamic storage modulus ( $E'$ ) at 80°C is preferably not more than 200 MPa, and the dynamic storage modulus ( $E'$ ) at 120°C is preferably not more than 150 MPa.

The dynamic storage modulus ( $E'$ ) here of the adhesive tape is measured in the following manner. That is, a test piece (width 10 mm, length 20 mm) is taken from an adhesive tape comprising a substrate (thickness 0.2 mm) and an adhesive layer formed thereon, and the dynamic viscoelastic behavior of this test piece at dispersed temperatures is measured with DMS200 (trademark, manufactured by Seiko Instruments) as a measurement apparatus under the measurement conditions of method: extension mode, temperature rise: 2°C/min, frequency: 1 Hz.

The dynamic storage modulus ( $E'$ ) of the adhesive tape is free from an effect of the adhesive layer. That is, the presence of an adhesive layer does not change the value of the dynamic storage modulus ( $E'$ ), and the dynamic storage modulus ( $E'$ ) is substantially that of the substrate.

In the present invention, an adhesive tape (substrate) having "a dynamic storage modulus ( $E'$ ) at 80°C of not less than 25 MPa and a dynamic storage modulus ( $E'$ ) at 120°C of not less than 10 MPa" can be obtained by using the above-mentioned Component A and Component B as olefin polymers together with a flame retardant, by appropriately determining the kind, mixing weight ratio, combination and the like of Component A and Component B, by using Component B having a specific dynamic storage modulus ( $E'$ ), by using Component A having a specific melting point, and the like.



The present invention is explained in detail in the following by referring to Examples and Comparative Examples. The present invention is not limited by these examples.

#### Materials used

- 5 Component A (thermoplastic resin having a carbonyl oxygen atom in the molecular skeleton)
- A1: ethylene-vinyl acetate copolymer (EVA), melting point 84°C (trademark: EVAFLEX P-1905, Du Pont-Mitsui Polychemicals Company, Ltd.)
- 10 A2: ethylene-ethyl acrylate copolymer (EEA), melting point 84°C (trademark: EVAFLEX A-702, Du Pont-Mitsui Polychemicals Company, Ltd.)
- Component B (polymer alloy containing an ethylene component and a propylene component)
- 15 B1: CATALLOY KS-353P (trademark, Montell SKD Sunrise Ltd.)
- B2: CATALLOY KS-021P (trademark, Montell SKD Sunrise Ltd.)
- B3: CATALLOY C200F (trademark, Montell SKD Sunrise Ltd.)

The dynamic storage moduli (E') at 23°C, 80°C and 120°C of the above-mentioned B1 - B3 are as follows:

- 20 B1 (23°C: 210 MPa, 80°C: 52 MPa, 120°C: 21 MPa)
- B2 (23°C: 294 MPa, 80°C: 125 MPa, 120°C: 59 MPa)
- B3 (23°C: 303 MPa, 80°C: 65 MPa, 120°C: 20 MPa)
- Component C (flame retardant)
- C1: magnesium hydroxide ( $Mg(OH)_2$ ) (trademark: Magshizu N-3, 25 Konoshima Chemical Industrial Co., Ltd.)
- C2-1: red phosphous (trademark: Hishigard CP-A15, The Nippon Chemical Industrial Co., Ltd.)
- C2-2: red phosphous (trademark: Norbaexcell F5, Phosphorus Chemical Industry Co., Ltd.)
- 30 C3: carbon black (trademark: Shisuto 3H, TOKAI CARBON CO., LTD.)
- Preparation of substrate and adhesive tape

The above-mentioned Component A, Component B and Component C were dry blended, kneaded in a pressurized 3L kneader at 180°C and pelleted. The composition was formed into a 0.2 mm thick 35 film by a T die extruder to give a substrate. One side surface of the substrate was subjected to a corona discharge treatment and an acrylic adhesive prepared by the following method was applied (thickness 30  $\mu m$ ) to give an adhesive tape.

### Preparation of acrylic adhesive

In a reaction vessel equipped with a condenser, a nitrogen inlet, a thermometer and a stirrer were placed, in a toluene solvent, 2-ethylhexyl acrylate (100 parts by weight), acrylic acid (2 parts by weight), and benzoyl peroxide (0.2 part by weight) as a polymerization initiator, and the mixture was allowed to react at 60°C for 8 hours to give a polymer. To this polymer solution was added a polyisocyanate crosslinking agent (trademark: CORONATE L, NIPPON POLYURETHANE INDUSTRY CO., LTD., 3 parts by weight per 100 parts by weight of the polymer solid content) to give an acrylic adhesive.

#### **Examples 1 - 7**

From Component A, Component B and Component C of the materials and amounts shown in the following Table 1, a substrate (adhesive tape) was prepared according to the above-mentioned forming method.

#### **Comparative Example 1**

Using Component A (A1: 100 parts by weight) but without using Component B or Component C, a substrate (adhesive tape) was prepared according to the above-mentioned forming method.

#### **Comparative Example 2**

Using Component A (A2: 100 parts by weight) but without using Component B or Component C, a substrate (adhesive tape) was prepared according to the above-mentioned forming method.

#### **Comparative Example 3**

Using Component B (B1: 100 parts by weight) but without using Component A or Component C, a substrate (adhesive tape) was prepared according to the above-mentioned forming method.

#### **Comparative Example 4**

Using polypropylene (PP) (100 parts by weight, trademark: NOVATEC FX3, Japan Polychem Corporation) but without using Component A, Component B or Component C, a substrate (adhesive tape) was prepared according to the above-mentioned forming method.

#### **Comparative Example 5**

Using Component A (A1: 100 parts by weight) and Component C (C1: 50 parts by weight) but without using Component B, a substrate (adhesive tape) was prepared according to the above-

mentioned forming method.

#### **Comparative Example 6**

Using Component A (A1: 100 parts by weight) and Component C (C1: 100 parts by weight) but without using Component B, a substrate (adhesive tape) was prepared according to the above-mentioned forming method.

#### **Comparative Example 7**

Using Component A (A1: 100 parts by weight) and Component C (C1: 105 parts by weight, C2-1: 5 parts by weight) but without using Component B, a substrate (adhesive tape) was prepared according to the above-mentioned forming method.

#### **Comparative Example 8**

Using Component A (A1: 100 parts by weight) and Component C (C1: 50 parts by weight, C2-2: 4 parts by weight, C3: 2 parts by weight) but without using Component B, a substrate (adhesive tape) was prepared according to the above-mentioned forming method.

#### Evaluation Test

The substrates (adhesive tapes) of Examples 1 - 7 and Comparative Examples 1 - 8 were subjected to the following evaluation tests. The dynamic storage moduli ( $E'$ ) at 80°C and 120°C of the adhesive tape were measured by the aforementioned method.

#### Evaluation of flame resistance

At the step of forming into a 3 mm thick sheet using a press machine during the formation of the aforementioned substrate, a test piece (size: length 70 mm, width 6.5 mm) was taken from the sheet and this test piece was burnt according to the incineration test method of polymer material by the oxygen index method according to JIS K 7201 to examine if the test piece continued to burn for 3 minutes or longer. In addition, the amount of minimum oxygen flow necessary for continuous flame burning of not less than 50 mm thereof after flame burning, and the nitrogen flow at that time were measured by a flowmeter (Candle Type Flammability Tester, TOYO SEIKI SEISAKU-SHO Co., Ltd.). The oxygen index was calculated from the following formula (I) and the flame resistance was evaluated based on the oxygen index. The flame resistance of not less than 25% was an

acceptance value and less than 25% was a rejection value.

$$\text{Oxygen index (O.I.)} = \left\{ \frac{[\text{O}_2]}{([\text{O}_2] + [\text{N}_2])} \right\} \times 100 \quad (\text{I})$$

wherein  $[\text{O}_2]$  is an oxygen flow (l/min) and  $[\text{N}_2]$  is a nitrogen flow (l/min).

5 Evaluation of resistance to thermal deformation and stretchability

To evaluate resistance to thermal deformation, the thermal deformation of an adhesive tape was measured by the aforementioned method, wherein the thermal deformation of not more than 65% was an acceptance value. To evaluate stretchability, the elongation at break of the adhesive tape was measured by the aforementioned method, wherein the elongation at break of not less than 150% was an acceptance value.

15 These evaluation results and the dynamic storage moduli ( $E'$ ) at 80°C and 120°C of the adhesive tape are shown in the following Table 1.

Table 1

	Component A		Component B		Component C				Elonga- tion at break (%)	Thermal deforma- tion (%)	Dynamic storage modulus (E')		Oxygen index (%)
	Kind	Amount added	Kind	Amount added	C1	C2		C3					
						Amount added	Kind				Amount added		
Example 1	A2	60	B1	40	100	C2-1	8	2	390	58	19	31	
Example 2	A1	50	B1	50	100	C2-2	8	2	310	45	23	32	
Example 3	A1	20	B1	80	100	C2-2	8	2	270	23	27	30	
Example 4	A1	20	B1	80	80	C2-2	8	2	470	25	25	28	
Example 5	A1	20	B2	80	100	C2-2	8	2	220	23	79	30	
Example 6	A1	20	B3	80	100	C2-2	8	2	230	23	40	29	
Example 7	A2	20	B1	80	50	C2-1	8	2	290	34	15	28	
Com. Ex. 1	A1	100	-	-	-	-	-	-	720	100	※	20	
Com. Ex. 2	A2	100	-	-	-	-	-	-	720	100	※	20	
Com. Ex. 3	-	-	B1	100	-	-	-	-	820	19	21	18	
Com. Ex. 4	-	-	PP	100	-	-	-	-	630	5	42	17	
Com. Ex. 5	A1	100	-	-	50	-	-	-	760	100	※	22	
Com. Ex. 6	A1	100	-	-	100	-	-	-	610	100	※	24	
Com. Ex. 7	A1	100	-	-	105	C2-1	5	-	280	100	※	38	
Com. Ex. 8	A1	100	-	-	50	C2-2	4	2	820	100	※	32	

In the Table, the amounts of Component A, Component B and Component C are in parts by weight, and ※ means that the adhesive tape (substrate) was melted and the dynamic storage modulus (E') could not be measured. The thermal deformation of 100% means that an adhesive tape was melted and dropped from the round bar, thus failing to maintain the shape of a tape. The polypropylene (PP) used in Comparative Example 4 is conveniently listed in the column of Component B.

As is evident from the foregoing explanation, the substrate for an adhesive tape of the present invention contains an olefin polymer and a flame retardant but substantially no halogen atom, and the adhesive tape has a thermal deformation at 100°C of not more than 65% and an elongation at break of not less than 150% at a tension speed of 300 mm/min. Consequently, the adhesive tape has suitable flexibility, a high level of stretchability and a high level of resistance to thermal deformation, despite the existence of the flame retardant, and a high level of flame resistance, and is free of generation of dioxin and toxic gas, such as chlorine gas, upon incineration.

This adhesive tape can be sufficiently used as a substitute for an adhesive tape using a PVC substrate, which has been used as an insulating tape for electric equipment used in the fields of vehicles, such as automobile, train, bus and the like, aircraft, ship, house, plant and the like. Inasmuch as it is free of generation of dioxin and toxic gas upon incineration and places less burden on the environment, the adhesive tape is highly valuable for use.

This application is based on a patent application Nos. 314103/1999 and 0288649/2000 filed in Japan, the contents of which are hereby incorporated by reference.

**WHAT IS CLAIMED IS**

1. An adhesive tape comprising a substrate and an adhesive layer formed on at least one side of the substrate, wherein the substrate comprises an olefin polymer and a flame retardant, but substantially no halogen atom, and the adhesive tape has a thermal deformation at 100°C of not more than 65%.

2. The adhesive tape of claim 1, which has an elongation at break of not less than 150% at a tension speed of 300 mm/min.

3. The adhesive tape of claim 1 or claim 2, wherein the olefin polymer comprises the following Component A and Component B:

Component A: a thermoplastic resin having a carbonyl oxygen atom in the molecular skeleton

Component B: a polymer alloy containing an ethylene component and a propylene component.

4. The adhesive tape of claim 3, wherein the Component B has a dynamic storage modulus (E') at 80°C of not less than 40 MPa and less than 180 MPa, and a dynamic storage modulus (E') at 120°C of not less than 12 MPa and less than 70 MPa.

5. The adhesive tape of claim 3, wherein the Component B has a dynamic storage modulus (E') at 23°C of not less than 200 MPa and less than 400 MPa.

6. The adhesive tape of claim 3, wherein the Component A is an ethylene copolymer or a metal salt thereof, having a melting point of not more than 120°C, which is obtained by polymerizing a vinyl ester compound, or an  $\alpha,\beta$ -unsaturated carboxylic acid or a derivative thereof, or the vinyl ester compound and the  $\alpha,\beta$ -unsaturated carboxylic acid or a derivative thereof.

7. The adhesive tape of claim 3, wherein the Component A and the Component B are mixed at a weight ratio (A:B) of 1:9 - 8:2.

8. The adhesive tape of claim 1 or claim 2, wherein the flame retardant is added in an amount of 20 - 200 parts by weight per

100 parts by weight of the olefin polymer.

9. The adhesive tape of claim 1 or claim 2, wherein the flame retardant is a metal hydroxide.

5

10. The adhesive tape of claim 1 or claim 2, which has a dynamic storage modulus (E') at 80°C of not less than 25 MPa and a dynamic storage modulus (E') at 120°C of not less than 10 MPa.

10 11. The adhesive tape of claim 1 or claim 2, wherein the substrate is not crosslinked during or after a forming process thereof.

12. A substrate for an adhesive tape, which comprises an olefin polymer and a flame retardant, but substantially no halogen atom, wherein the olefin polymer comprises the following Component A and Component B:

Component A: a thermoplastic resin having a carbonyl oxygen atom in the molecular skeleton

Component B: a polymer alloy containing an ethylene component and a propylene component.

13. The substrate of claim 12, wherein the Component B has a dynamic storage modulus (E') at 80°C of not less than 40 MPa and less than 180 MPa, and a dynamic storage modulus (E') at 120°C of not less than 12 MPa and less than 70 MPa.

14. The substrate of claim 12, wherein the Component B has a dynamic storage modulus (E') at 23°C of not less than 200 MPa and less than 400 MPa.

15. The substrate of claim 12, wherein the Component A is an ethylene copolymer or a metal salt thereof, having a melting point of not more than 120°C, which is obtained by polymerizing a vinyl ester compound, or an  $\alpha,\beta$ -unsaturated carboxylic acid or a derivative thereof, or the vinyl ester compound and the  $\alpha,\beta$ -unsaturated carboxylic acid or a derivative thereof.



16. The substrate of claim 12, wherein the Component A and the Component B are mixed at a weight ratio (A:B) of 1:9 - 8:2.

5 17. The substrate of claim 12, wherein the flame retardant is added in an amount of 20 - 200 parts by weight per 100 parts by weight of the olefin polymer.

18. The substrate of claim 12, wherein the flame retardant is a metal hydroxide.

10

19. The substrate of claim 12, which has a dynamic storage modulus (E') at 80°C of not less than 25 MPa and a dynamic storage modulus (E') at 120°C of not less than 10 MPa.

15 20. The substrate of claim 12, which is not crosslinked during or after a forming process thereof.

# ABSTRACT OF THE DISCLOSURE

The present invention provides an adhesive tape containing a substrate and an adhesive layer formed on at least one side of the substrate, wherein the substrate contains an olefin polymer and a flame retardant, but substantially no halogen atom, and the adhesive tape has a thermal deformation at 100°C of not more than 65%. The present invention also provides a substrate containing an olefin polymer and a flame retardant, but substantially no halogen atom, wherein the olefin polymer contains the following Component A and Component B:

Component A: a thermoplastic resin having a carbonyl oxygen atom in the molecular skeleton

Component B: a polymer alloy containing an ethylene component and a propylene component.

The adhesive tape and the substrate for the adhesive tape of the present invention are free of generation of dioxin and toxic gas upon incineration, and show superior resistance to thermal deformation, flame resistance and superior stretchability in combination.



**COMBINED DECLARATION AND POWER OF ATTORNEY**

As below named inventor, I hereby declare that

This declaration is of the following type:

- ☒ original ☐ design ☐ supplemental  
☐ national stage of PCT  
☐ divisional ☐ continuation ☐ continuation-in-part

My residence, post office address, and citizenship are as stated below next to my name. I believe I am the original, first, and sole inventor (*if only one name is listed below*) or an original, first, and joint inventor (*if plural names are listed below*) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

**ADHESIVE TAPE AND SUBSTRATE FOR ADHESIVE TAPE**

the specification of which:

- ☒ is attached hereto.  
☐ was filed on \_\_\_\_\_ as Application No. \_\_\_\_\_ and was amended on \_\_\_\_\_ (*if applicable*).  
☐ was filed by Express Mail No. \_\_\_\_\_, as Application No. not known yet, and was amended on \_\_\_\_\_ (*if applicable*).  
☐ was described and claimed in PCT International Application No. \_\_\_\_\_ filed on \_\_\_\_\_ and as amended pursuant to PCT Article 19 on \_\_\_\_\_ (*if any*).

I state that I have reviewed and understand the contents of the above-identified specification, including the claim(s), as amended by any amendment referred to above.

I acknowledge the duty to disclose information that is material to the patentability of this application in accordance with 37 C.F.R. § 1.56.

I claim foreign priority benefits under 35 U.S.C. § 119 of any foreign application(s) for patent or inventor's certificate or of any PCT international application(s) designating at least one country other than the United States of America listed below and have also identified below any foreign application(s) for patent, utility model, design registration, or inventor's certificate or any PCT international application(s) designating at least one country other than the United States of America filed by me on the same subject matter having a filing date before that of the application(s) of which priority is claimed.

PRIOR FOREIGN PATENT, UTILITY MODEL, AND DESIGN REGISTRATION APPLICATIONS						
COUNTRY	APPLICATION	DATE OF FILING (day,month,year)	PRIORITY CLAIMED UNDER 35 U.S.C. § 119			
Japan	314103/1999	04/11/1999	X	YES		NO
Japan	288649/2000	22/09/2000	X	YES		NO
				YES		NO

I claim the benefit pursuant to 35 U.S.C. § 119(e) of the following United States provisional application(s):

PRIOR U.S. PROVISIONAL APPLICATIONS BENEFIT CLAIMED UNDER 35 U.S.C. 119(e)	
APPLICATION NO.	DATE OF FILING (day,month,year)

1. Demographic characteristics	
Age (years)	50.0
Gender	Male
Marital status	Married
Education	High school
Occupation	Unemployed
Income (USD)	1000
Health status	Good
Smoking status	Non-smoker
Alcohol consumption	Occasional
Exercise frequency	Regular
Stress level	Low
Family size	3
Religious beliefs	Christian
Political views	Conservative
Travel frequency	Monthly
Food preferences	Vegetarian
Sleeping habits	Regular
Work hours	Full-time
Commuting time	30 minutes
Living environment	Urban
Neighborhood safety	Safe
Access to healthcare	Good
Health insurance	Private
Medical history	None
Current medications	None
Family medical history	None
Genetic testing results	None
Psychological state	Stable
Mental health	Good
Emotional stability	High
Personality traits	Introverted
Interests and hobbies	Reading
Social life	Active
Relationship status	Married
Parental status	Parent
Childhood experiences	Positive
Adulthood experiences	Challenging
Life goals	Stable
Values and beliefs	Traditional
Worldview	Optimistic
Philosophy of life	Simple
Religious practices	Regular
Political participation	Active
Cultural engagement	High
Artistic interests	Low
Scientific interests	High
Technological interests	Medium
Environmental concerns	High
Animal welfare	Concerned
Human rights	Supportive
Global issues	Interested
Local community	Involved
Neighborhood issues	Concerned
City planning	Interested
Transportation	Concerned
Public services	Appreciative
Education system	Critical
Healthcare system	Appreciative
Justice system	Critical
Government	Disappointed
Corruption	Concerned
Transparency	Interested
Accountability	Concerned
Efficiency	Interested
Effectiveness	Concerned
Responsiveness	Interested
Accessibility	Concerned
Equity	Interested
Inclusivity	Concerned
Participation	Interested
Representation	Concerned
Responsibility	Interested
Transparency	Concerned
Accountability	Interested
Efficiency	Concerned
Effectiveness	Interested
Responsiveness	Concerned
Accessibility	Interested
Equity	Concerned
Inclusivity	Interested
Participation	Concerned
Representation	Interested
Responsibility	Concerned
Transparency	Interested
Accountability	Concerned
Efficiency	Interested
Effectiveness	Concerned
Responsiveness	Interested
Accessibility	Concerned
Equity	Interested
Inclusivity	Concerned
Participation	Interested
Representation	Concerned
Responsibility	Interested
Transparency	Concerned
Accountability	Interested
Efficiency	Concerned
Effectiveness	Interested
Responsiveness	Concerned
Accessibility	Interested
Equity	Concerned
Inclusivity	Interested
Participation	Concerned
Representation	Interested
Responsibility	Concerned
Transparency	Interested
Accountability	Concerned
Efficiency	Interested
Effectiveness	Concerned
Responsiveness	Interested
Accessibility	Concerned
Equity	Interested
Inclusivity	Concerned
Participation	Interested
Representation	Concerned
Responsibility	Interested
Transparency	Concerned
Accountability	Interested
Efficiency	Concerned
Effectiveness	Interested
Responsiveness	Concerned
Accessibility	Interested
Equity	Concerned
Inclusivity	Interested
Participation	Concerned
Representation	Interested
Responsibility	Concerned
Transparency	Interested
Accountability	Concerned
Efficiency	Interested
Effectiveness	Concerned
Responsiveness	Interested
Accessibility	Concerned
Equity	Interested
Inclusivity	Concerned
Participation	Interested
Representation	Concerned
Responsibility	Interested
Transparency	Concerned
Accountability	Interested
Efficiency	Concerned
Effectiveness	Interested
Responsiveness	Concerned
Accessibility	Interested
Equity	Concerned
Inclusivity	Interested
Participation	Concerned
Representation	Interested
Responsibility	Concerned
Transparency	Interested
Accountability	Concerned
Efficiency	Interested
Effectiveness	Concerned
Responsiveness	Interested
Accessibility	Concerned
Equity	Interested
Inclusivity	Concerned
Participation	Interested
Representation	Concerned
Responsibility	Interested
Transparency	Concerned
Accountability	Interested
Efficiency	Concerned
Effectiveness	Interested
Responsiveness	Concerned
Accessibility	Interested
Equity	Concerned
Inclusivity	Interested
Participation	Concerned
Representation	Interested
Responsibility	Concerned
Transparency	Interested
Accountability	Concerned
Efficiency	Interested
Effectiveness	Concerned
Responsiveness	Interested
Accessibility	Concerned
Equity	Interested
Inclusivity	Concerned
Participation	Interested</

PRIOR U.S. APPLICATIONS OR PCT INTERNATIONAL PATENT APPLICATIONS  
DESIGNATING THE U.S. FOR BENEFIT UNDER 35 U.S.C. 120

U.S. APPLICATIONS		Status ( <i>check one</i> )		
APPLICATION NO.	U.S. FILING DATE	PATENTED	PENDING	ABANDONED
1. 0/				
2. 0/				
3. 0/				

PCT APPLICATIONS DESIGNATING THE U.S.	Status (check one)
---------------------------------------	--------------------

PCT APPLICATION NO.	PCT FILING DATE (day,month,year)	U.S. APPLN. NOS. ASSIGNED (if any)	PATENTED	PENDING	ABANDONED
4.					
5.					
6.					

DETAILS OF FOREIGN APPLICATIONS FROM WHICH PRIORITY CLAIMED  
UNDER 35 U.S.C. §119 FOR ABOVE LISTED U.S./PCT APPLICATIONS

ABOVE APPLN. NO.	COUNTRY	APPLICATION NO.	DATE OF FILING (day,month,year)	DATE OF ISSUE (day,month,year)
1.				
2.				
3.				
4.				
5.				
6.				

As a named inventor, I hereby appoint Leydig, Voit & Mayer, Ltd. to prosecute this application and transact all business in the Patent and Trademark Office connected therewith: Customer Number 23460.



**23460**

PATENT TRADEMARK OFFICE

I further direct that correspondence concerning this application be directed to Leydig, Voit & Mayer, Ltd.: Customer Number 23460.



**23460**

PATENT TRADEMARK OFFICE

I declare that all statements made herein of my own knowledge are true, that all statements made on information and belief are believed to be true, that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code, and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Full name of first inventor: Yoshio NAKAGAWA

Inventor's signature Yoshio Nakagawa

Date October 16, 2000

Country of Citizenship: Japan

Residence: Ibaraki-shi, Osaka, Japan

Post Office Address: c/o Nitto Denko Corporation, 1-2, Shimohozumi 1-chome, Ibaraki-shi,  
Osaka 567-8680 Japan

Full name of second joint inventor: Shigeki ISHIGURO

Inventor's signature Shigeki Ishiguro

Date October 16, 2000

Country of Citizenship: Japan

Residence: Ibaraki-shi, Osaka, Japan

Post Office Address: c/o Nitto Denko Corporation, 1-2, Shimohozumi 1-chome, Ibaraki-shi,  
Osaka 567-8680 Japan

Full name of **third joint inventor**: Masayoshi NATSUME

Inventor's signature Masayoshi Natsume

Date October 16, 2000 Country of Citizenship: Japan

Residence: Ibaraki-shi, Osaka, Japan

Post Office Address : c/o Nitto Denko Corporation, 1-2, Shimohozumi 1-chome, Ibaraki-shi,  
Osaka 567-8680 Japan

Full name of **forth joint inventor**: Shinichi TAKADA

Inventor's signature Shinichi Takada

Date October 16, 2000 Country of Citizenship: Japan

Residence: Ibaraki-shi, Osaka, Japan

Post Office Address: c/o Nitto Denko Corporation, 1-2, Shimohozumi 1-chome, Ibaraki-shi,  
Osaka 567-8680 Japan

Full name of **fifth joint inventor**: Kooki OYAMA

Inventor's signature Kooki Oyama

Date October 16, 2000 Country of Citizenship: Japan

Residence: Ibaraki-shi, Osaka, Japan

Post Office Address: c/o Nitto Denko Corporation, 1-2, Shimohozumi 1-chome, Ibaraki-shi,  
Osaka 567-8680 Japan

Full name of **sixth joint inventor**: Hajime YANAGIDA

Inventor's signature Hajime Yanagida

Date October 16, 2000 Country of Citizenship: Japan

Residence: Ibaraki-shi, Osaka, Japan

Post Office Address: c/o Nitto Denko Corporation, 1-2, Shimohozumi 1-chome, Ibaraki-shi,  
Osaka 567-8680 Japan